

PRIME DISPLAY FABRIC CLASSIC



PRODUCT: ST-117T/ST-117D

FEATURES:

- Special tight structure makes it with high opacity even at a much lighter weight compared with other display textile fabric
- Truly wrinkle free, can recover quickly after folded, makes it easy for transportation
- Soft, smooth, has good textile hand feel
- Can be coated for Dye-sub direct, Dye-sub transfer printing, also with good printing images by Latex inks

APPLICATIONS:

-Display Pop-up Backdrops



MATERIAL DETAILS

PROPERTIES	TEST METHOD	METRIC	IMPERIAL
Total Weight	DIN EN ISO 2286-2, ASTM D751	220 g/sq.m	6.4 oz/sq.yd
Base Fabric	DIN 60001, ASTM D7641	Polyester	Polyester
Weave Method	N/A	Warp-knitted 3 bar	
Shrinkage	N/A	≤ 2% (210°C, 30s)	
Obscuring Ratio	ANSI PH2.19, ISO 5/2	(50±4)%	
Flame Resistance	DIN 4102-1-B1, NFPA 701 Test1,NF P92 M1	DIN 4102-1-B1, NFPA 701 Test1, NF P92 M1	
Recommend Fixation Temperature	N/A	190°C-210°C, 1-2min	
Yellowing Temperature	SUPRKC REX-C400, 30s	≥ 210°C	
Width	DIN EN ISO 3759, ASTM D751-2006	Max 320cm	126"
Standard Length	DIN EN ISO 3759, ASTM D751-2006	50m	55yds

INK PRINTABILITY

Solvent	Eco Solvent	UV	Latex
			<input type="checkbox"/>
Screen Printing	Dye Transfer	Dye Direct	
	<input type="checkbox"/>	<input type="checkbox"/>	

NOTE: It is normal that the weight of most products will have an average fluctuation of 5%. All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of warranty.

CGS Imaging Inc.

6950 Hall Street
 Holland Ohio 43528
www.cgs-imaging.com

P. 419.897.3000
 F. 419.893.4316